

AMENDMENT NO. 2 SEPTEMBER 2017
TO
IS 16208 : 2015 TEXTILES — HIGH DENSITY
POLYETHYLENE (HDPE)/POLYPROPYLENE (PP)
WOVEN SACKS FOR PACKAGING 10 kg,
15 kg, 20 kg, 25 kg AND 30 kg FOODGRAINS —
SPECIFICATION

[Page 2, Table 1, Sl No. (i)] — Delete.

[Page 2, Table 1, Sl No. (viii)] — Substitute the following for the existing:

Sl No.	Characteristic	Requirement					Tolerance	Method of Test, Ref to
		Type I	Type II	Type III	Type IV	Type V		
(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)
viii)	Elongation at break of the fabric, percent:							IS 1969 (Part 1)
	a) Lengthwise	15 to 25	15 to 25	15 to 25	15 to 25	15 to 25	—	
	b) Widthwise	15 to 25	15 to 25	15 to 25	15 to 25	15 to 25	—	

(Page 6, clause **D-1**, lines 4 and 5) — Substitute ‘590°C’ for ‘550°C’.

(Page 6, clause **D-2.5**, line 2) — Substitute ‘590°C’ for ‘550°C’.

(Page 6, clause **D-4.1**, line 1) — Substitute ‘590°C’ for ‘550°C’.

(Page 6, clause **D-4.5**, line 2) — Substitute ‘590°C’ for ‘550°C’.