

AMENDMENT NO. 1 JUNE 2025
TO
IS 16270 : 2023 SECONDARY CELLS AND BATTERIES FOR SOLAR
PHOTOVOLTAIC APPLICATION — GENERAL REQUIREMENTS AND
METHODS OF TEST
(First Revision)

[Foreword, Para 4, Point a)] — Substitute **4.3.3 a)** for **4.3.2 a)**.

(Page 1, clause **1**, Para 3) — Substitute the following for the existing:

‘This standard is applicable to all types of secondary cells and batteries used in solar photovoltaic off-grid applications.’

(Page 7, clause **8.4.3.2**, Para 2) — Substitute the following for the existing:

‘The steps a) and b) shall be repeated 99 times.’

(Page 7, clause **8.4.3.2**, Para 3) — Substitute the following for the existing:

‘At the termination of the 99th execution of step b) the test battery shall be subjected to a residual capacity determination according to **8.4.4**.’

[Page 8, clause **8.4.4**, Point b)] — Substitute the following for the existing:

‘b) The residual capacity test for lead acid and other batteries shall be carried out with the I_{10} current to $1.80\text{ V} \times n$ cells for lead acid batteries and at the 0.2 I_t current to $1.00\text{ V} \times n$ cells for nickel-cadmium, and Ni-MH batteries. For lithium batteries discharge is to be carried out at 0.2 I_t current. For lithium batteries and other batteries, the end voltages are defined by the battery manufacturer;’

(Page 9, Table 6) — Substitute ‘**Cell/battery**’ for ‘**Battery**’.