

**AMENDMENT NO. 1 NOVEMBER 2015
TO
IS/ISO 16037 : 2002 RUBBER CONDOMS FOR CLINICAL TRIALS —
MEASUREMENT OF PHYSICAL PROPERTIES**

(Page 2, clause 6.2) — Substitute the following for the existing clause:

‘Measure at least 13 condoms, using a flat-footed micrometer, dial — or digital-type, measurement intervals of not larger than 0.001 mm, with a foot pressure set at 22 ± 5 kPa. The recommended foot diameter is 5 ± 2 mm. The procedure is as described in ISO 4074.’

(Page 2, clause 6.3, line 1) — Substitute ‘using the mass method’ for ‘using the weighing method’.

(Page 2, clause 6.3, para 2) — Substitute ‘The procedure for determining the thickness is as described in ISO 4074’ for ‘para, equation and note’.

(Page 2, clause 8, line 1) — Substitute ‘at least 500 condoms’ for ‘at least 315 condoms’ and delete ‘(but preferably 500)’.

(Page 2, clause 8, para 2) — Substitute the following note for existing para:

‘NOTE — Data can be summarized as histograms (or stem-and-leaf diagrams). The aim of the test is not only to determine whether the lot (s) of products being used in the investigation comply with ISO 4074, but also to reliably estimate the mean, range, standard deviation, and number of non-compliers. For a more reliable estimate of lot defectiveness, it is advisable that at least 2 000 condoms be tested.’

(Page 3, clause 12, line 4) — Substitute ‘allergenicity, date of manufacture, etc’ for ‘allergenicity, etc.’

(Page 4, clause 13) — Insert the following note at the end of the clause:

‘NOTE — If the clinical trial is examining the relationship between performance or acceptance against the physical properties of the condom, then it is important to keep track of changes in these properties during the course of the trial, and to take appropriate action, if necessary. If the trial relies on continuing compliance with ISO 4074, it is important to verify that the physical properties have not dropped to the extent that compliance is at risk.’