

AMENDMENT NO. 1 JULY 1975
TO
IS : 5207 - 1969 SPECIFICATION FOR
BRUSHES, CLOTHES

Alteration

(Page 3, clause 4.1.2.3) — Substitute the following for the existing clause:

'4.1.2.3 The timber shall be reasonably straight-grained and well-seasoned to a moisture content not exceeding 15 percent when tested by the electronic moisture meter method. In case of dispute, the oven-dry method shall be used (see Appendix C).'

Addendum

(Page 9, clause B-3.4.1) — Add the following new appendix after B-3.4.1:

APPENDIX C
(Clause 4.1.2.3)

DETERMINATION OF MOISTURE CONTENT OF TIMBER

C-1. TEST SPECIMEN

C-1.1 The entire block used in brushes, clothes, may form the test specimen for the determination of moisture content, or a coupon cut from the test specimen may, as well, be used for moisture content determination. When for any reason additional determination of moisture content is required, separate samples shall be prepared from the sample material as is used in preparing the test specimens. Smaller specimens may be used when deemed necessary. The test shall be carried out immediately after cutting the specimen.

C-2. PROCEDURE

C-2.1 Weigh accurately each test specimen. This specimen shall then be dried in a ventilated oven at a temperature of $105 \pm 2^{\circ}\text{C}$ until the weight becomes constant between two successive weighings made at an interval of not less than one hour.

C-3. CALCULATION

C-3.1 Moisture content, expressed as a percentage of the oven-dry mass = $100 \times \frac{W_1 - W_0}{W_0}$

where

W_1 = initial mass in g of the test specimen, and

W_0 = oven-dry mass in g of the test specimen.

(CDC 31)