

AMENDMENT NO. 2 JANUARY 1998
TO
IS 5297 : 1977 SPECIFICATION FOR
PERCHLOROETHYLENE
(TETRACHLOROETHYLENE), TECHNICAL
(First Revision)

[Page 4, Table 1, Sl No. (iii), col 2 and 3] — Substitute the following for the existing:

(2)	(3)
Distillation range at 760 mm Hg	The difference between the temperatures (running points) at which 2 and 97 percent of the volume taken have been collected shall not exceed 2.5°C. The range shall include 121.2°C.

[Page 4, Table 1, Sl No. (v)] — Insert a new requirement as follows:

(1)	(2)	(3)	(4)
vi)	Resistance to corrosion	To pass the test	A-7

(Page 7, clause A-3.2, line 2) — Substitute 'Suitable heating media' for 'water-bath'.

(Page 7, clause A-3.3, line 4) — Substitute 'g' for 'mg'.

[Page 9, clause A-4.1.5(b), line 1] — Substitute 'sheet' for 'shelf'.

[Page 11, clause A-4.3.2(a) and (b)] — Substitute the following for the existing manner:

- 'a) For every 10 mm above 760 mmHg, subtract 0.47°C from the observed temperatures of the boiling range to get the specified temperature range at 760 mmHg.
- b) For every 10 mm below 760 mmHg, add 0.47°C to the observed temperatures of the boiling range to get the specified temperature range at 760 mmHg.'

Amend No. 2 to IS 5297 : 1977

(*Page 12, clause A-5.0, line 4*) — Insert 'with' between 'layer matches' and 'that of the'.

(*Page 14, clause A-5.3, line 2*) — Delete 'accurately weighed'.

(*Page 14, clause A-6.3.1*) — Insert a new clause A-7 after A-6.3.1:

A-7 TEST FOR RESISTANCE TO CORROSION

A-7.1 Apparatus

A-7.1.1 Microscope

Any suitable microscope which can magnify 20 times.

A-7.1.2 Carbon Steel Strips

50 mm × 10 mm of any other suitable size which is polished over smooth emery paper, cleaned and dried. The strips shall be free from any rust spot.

A-7.1.3 Glass Bottle — 500 ml.

A-7.2 Procedure

Take 200 ml of the material in a clean, dry glass bottle provided with a lid. Immerse the rust free polished carbon steel strips in the material and maintain in the same for 24 hours and observe under a suitable microscope (× 20) for any rust spots that might have developed.

A-7.3 The material shall be taken to have passed the test if no rust spots are observed on the steel strips.

(PCD 9)