

AMENDMENT NO. 2 DECEMBER 2016
TO
IS 5306 : 1996 SODIUM CARBOXYMETHYL CELLULOSE,
FOOD GRADE — SPECIFICATION

(Second Revision)

(Page 1, *clause 2*) — Insert the following at the end:

<i>IS No.</i>	<i>Title</i>
9497 : 1980	Method for determination of sodium and potassium (flame photometric)
10614 : 1983	Method for atomic absorption spectrophotometric determination of sodium and potassium

(Page 2, *Table 1*) — Substitute the following for the existing:

Table 1 Requirements for Sodium Carboxymethyl Cellulose Food Grade
(*Clause 4.1.3*)

SI No.	Characteristics	Requirements	Methods of Test	Ref to
(1)	(2)	(3)	(4)	
i)	Purity as sodium carboxymethyl cellulose, percent by mass on dry basis, <i>Min</i>	99.5 ¹⁾	—	
ii)	Degree of substitution, <i>Max</i>	0.20 to 1.50	Annex B	
iii)	Loss on drying, percent by mass, <i>Max</i>	10	Annex C	
iv)	Sodium chloride on dry basis, percent by mass, <i>Max</i>	0.4	Annex D	
v)	Free glycolate on dry basis, percent by mass, <i>Max</i>	0.5	Annex E	
vi)	pH of 1 percent colloidal solution	6 to 8.5	—	
vii)	Lead (as Pb), mg/kg, <i>Max</i> .	2	15 of IS 1699	
viii)	Arsenic (as As), mg/kg, <i>Max</i> .	3	15 of IS 1699	
ix)	Heavy Metals, mg/kg, <i>Max</i>	40	Annex F	
x)	Combined sodium chloride and free glycolate on dry basis, percent by mass, <i>Max</i>	0.5 ²⁾	—	
xi)	Sodium, percent by mass (on dry basis), <i>Min</i>	12.4 ³⁾	IS 9497 or IS 10614	
¹⁾ Purity is determined by subtracting from 100, the percentage of combined sodium chloride and free glycolate.				
²⁾ Obtained by the simple addition of values obtained at SI No. (iv) and (v)				
³⁾ In case of dispute, the test method as given in IS 10614 shall be the reference method.				

(FAD 08)

Publication Unit, BIS, New Delhi, India