

**AMENDMENT NO. 1 MARCH 2013
TO
IS 5325 : 1989 BOX PALLETS FOR THROUGH TRANSIT OF
GOODS — METHODS OF TEST**

(First Revision)

(Page 1, clause 3.3) — Insert the following at the end of the clause:

‘This test is also required for stackable injection moulded plastic box pallet made of HDPE/PP/Structural foam HDPE.’

(Page 1, clause 3.4) — Insert the following new clauses after the clause 3.4:

‘3.5 Drop Test of Box Pallet

A test for determination of resistance to drop box pallet.

3.6 Environmental Stress Crack Resistance Test of Box Pallet

A test for the strength of injection moulded plastic pallet against determination of environmental stress crack resistance over prolonged usages.

3.7 Dimensional Variation Test of Box Pallet

A test for the stability against dimensional variation/stability requirement of box pallet.’

(Page 1, clause 5.1.2) — Insert the following at the end of the clause:

‘Apply an equally distributed load corresponding to 1.25 times the maximum payload to the load carrying surface of the injection moulded box pallet made of HDPE/PP/Structural foam HDPE and measure the maximum deflection quantity of the load carrying surface.’

Amend No. 1 to IS 5325 : 1989

(Page 2, clause 5.3.3) — Insert the following new clauses after 5.3.3:

5.3.4 The comparison in the height of bin when tested shall not exceed 1 percent of its original height.

5.3.5 The specimen should recover by at least 50 percent after 24 h after removing the test load.

5.4 Drop Test

5.4.1 The empty specimen shall be lifted to a height of 4 m.

5.4.2 The empty specimen shall be dropped on base on concrete floor or steel plate.

5.4.3 Examine for any abnormalities/cracks.

5.5 Environmental Stress Crack Resistance Test

5.5.1 1 percent solution of suitable surface active agent at $80 \pm 1^\circ\text{C}$ to be prepared in a tank.

5.5.2 The empty specimen shall be submerged in the tank for 6 h.

5.5.3 Specimen shall be examined for any surface cracking.

5.6 Dimensional Variation Test

5.6.1 Note down the overall dimensions of the empty specimen.

5.6.2 Support the empty specimen on its base in air circulation at $80 \pm 1^\circ\text{C}$ for 30 min.

5.6.3 While the specimen is still supported on its base, allow it to cool at ambient temperature.

Amend No. 1 to IS 5325 : 1989

5.6.4 Calculate the percentage change in the dimension of the specimen, which should not exceed by ± 15 percent of the original dimensions.'

(Page 2, clause **6.1**) — Substitute the following for the existing:

6.1 The following shall be written in the test report:

- a) Type, class, load, dimensions and material used;
- b) Self weight;
- c) Temperature and humidity conditions during test;
- d) Summary of results of tests:
 - 1) Downward loading test;
 - 2) Horizontal loading test (This test is also applicable for box pallets fixed, folding/collapsible type box pallets made of HDPE/PP/Structural foam HDPE by injection moulding process);
 - 3) Superimposed loading/ stackability test;
 - 4) Drop test;
 - 5) Environment stress crack test; and
 - 6) Dimensional variation test
- e) Other information required.'