

AMENDMENT NO. 1 FEBRUARY 2024
TO
IS 5410 : 2013 CEMENT PAINT — SPECIFICATION
(Second Revision)

(Page 10, clause F-2.1) — Substitute the following for the existing paragraph:

‘Weigh accurately not less than 50 g of the sample and transfer to a 250 ml beaker. Mix the material to a thin paste with water. Thoroughly mix the contents of the beaker and break up all lumps with the flattened end of a stirring rod without grinding action. The test should be completed within one hour of making the paste as otherwise the material will thicken up in the process of setting.’