

AMENDMENT NO. 1 NOVEMBER 1992
TO
IS 5511 : 1991 COVERD ELECTRODES FOR MANUAL METAL ARC
WELDING OF CAST IRON — SPECIFICATION
(First Revision)

(Page 3, Table 5)—Substitute the following for the existing table:

Table 5 Chemical Composition
(Clause 7.3)

Symbol	FeC 1	FeC 2	NiFe	NiCu 1	NiCu 2	Ni	CuAl	CuSn 1	CuSn 2
Element	Composition of Core Wire, Percent ¹⁾								
C	3.25 to 3.50	0.15	2.0	0.35 to 0.55	0.35 to 0.55	2.0	—	—	—
Si	2.75 to 3.00	0.03	4.0	0.75	0.75	4.0	0.10	⁴⁾	⁴⁾
Mn	0.60 to 0.75	0.30 to 0.60	1.0	2.25	2.25	1.0	—	⁴⁾	⁴⁾
P	0.50 to 0.75	0.04	—	—	—	—	—	0.10 to 0.35	0.05 to 0.35
S	0.10	0.04	0.03	0.025	0.025	0.025	—	—	—
Fe	remainder	remainder	remainder	3.0 to 6.0	3.0 to 6.0	8.0	1.5	⁴⁾	⁴⁾
M	trace	—	—	—	—	—	—	—	—
Ni ²⁾	trace	—	45.0 to 60.0	50.0 to 60.0	60.0 to 70.0	85.0 Min	—	⁴⁾	⁴⁾
Cu ³⁾	—	—	2.50	35.0 to 45.0	25.0 to 35.0	2.50	remainder	remainder	remainder
Zn	—	—	—	—	—	—	0.02	⁴⁾	⁴⁾
Sn	—	—	—	—	—	—	—	4.0 to 6.0	7.0 to 9.0
Al	—	—	—	—	—	—	9.0 to 11.0	0.01 ⁴⁾	0.01 ⁴⁾
Pb	—	—	—	—	—	—	0.02	0.02 ⁴⁾	0.02 ⁴⁾
Total of other elements	—	—	1.00	1.00	1.00	1.00	0.50	0.50	0.50

1) Unless otherwise stated, single values represent maximum percentages.

2) Nickel plus incidental cobalt.

3) Copper plus incidental silver.

4) Total of other elements including those (foot-note 4), shall not exceed the specified value.'

(MTD 11)