

**AMENDMENT NO. 4 FEBRUARY 2005
TO
IS 5539 : 1969 SPECIFICATION FOR
PRESERVATIVE TREATED PLYWOOD**

(Page 4, clause 5.1.3) — Substitute 'Annex A' for 'Appendix A'.

(Page 5, clauses 5.1.4 and 5.2.1) — Substitute 'Annex B' for 'Appendix B'

(Page 7, clause 7.1) — Add the following new clauses after 7.1:

8 DIMENSIONS AND TOLERANCES

8.1 The dimensions of plywood boards shall be as given below:

2 400 mm × 1 200 mm	2 100 mm × 900 mm
2 100 mm × 1 200 mm	1 800 mm × 900 mm
1 800 mm × 1 200 mm	

8.2 Thickness

The thickness shall be 3 mm, 4 mm, 5 mm, 6 mm, 8 mm, 9 mm, 12 mm, 15 mm, 19 mm, 22 mm and 25 mm.

NOTE — Any other dimensions (length, width and thickness) as agreed to between the manufacturer and the purchaser may also be used

8.3 Tolerances

Tolerances on the nominal sizes of finished boards shall be as given below:

<i>Dimension</i>	<i>Tolerance</i>
Length	+6 -0 mm
Width	+3 -0 mm

Thickness:

i) Less than 6 mm	±10 percent
ii) 6 mm and above	±5 percent

Amend No. 4 to IS 5539 : 1969

Edge straightness	2 mm per 1 000 mm or 0.2 percent
Squareness	2 mm per 1 000 mm or 0.2 percent

NOTE — Edge straightness and squareness shall be tested as per Annex C.

9 STATIC BENDING STRENGTH

Three test specimens taken in each direction from the sample of plywood, when tested in accordance with IS 1734 (Part 11) : 1983⁹ shall have an average and a minimum individual Modulus of Elasticity and Modulus of Rupture not less than the values specified in Table 1.

Table 1 Average and Minimum Individual Values of Modulus of Elasticity (MOE) and Modulus of Rupture (MOR)
(Clause 9)

Direction	MOE (N/mm ²)		MOR (N/mm ²)	
	Average	Min. Ind.	Average	Min. Ind.
(1)	(2)	(3)	(4)	(5)
Along (Direction parallel to the grain direction of the face veneer)	5 000	4 500	40	36
Across (Direction perpendicular to the grain direction of the face veneer)	2 500	2 200	20	18

(Page 7, footnote) — Insert the following new footnote:

'Method of test for plywood Part 11 Determination of static bending strength (second revision).'

(Pages 7 and 8, clauses 8, 9, 10 and 11) — Renumber clause 8, 9, 10 and 11 as 10, 11, 12 and 13 and the sub-clauses, wherever they exist, accordingly.

(Page 8, clause 10.1) — Substitute 'Annex A' for 'Appendix A'

[Page 8, clause 11.1(c)] — Substitute 'Annex A' for 'Appendix A'.

Amend No. 4 to IS 5539 : 1969

(Page 9, Appendix A and the clause references thereunder) — Rename Appendix A as Annex A and substitute the clause references with 'Clauses 5.1.3, 5.1.4, 12.1 and 13.1(c)'

(Page 11, Appendix B and Table 1) — Rename **APPENDIX B** as **ANNEX B** and Table 1 as Table 2.

(Page 11, clause **B-1.1**, fourth line) — Substitute 'Table 2' for 'Table 1'

(Page 13, clause **B-3.1**, second line) — Substitute 'Table 2' for 'Table 1'.

(Page 13, clause **B-3.1.1**) — Insert the following Annex C after Annex B:

ANNEX C

(Clause 8.3)

METHOD OF TEST FOR EDGE STRAIGHTNESS AND SQUARENESS

C-1 PROCEDURE FOR EDGE STRAIGHTNESS

C-1.1 The straightness of the edges and ends of plywood shall be verified against a straight edge not less than the full length of the plywood. If the edge on the end of the plywood is convex, it shall be held against the straight edge in such a way as to give approximately equal gap at each end. The largest gap between the straight edge and the edge shall be measured to the nearest millimetre and recorded

C-2 PROCEDURE FOR SQUARENESS

C-2.1 The squareness of plywood shall be checked with a 1 200 mm × 1 200 mm square, by applying one arm of the square to the plywood. The maximum width of the gap shall be recorded.

(CED 20)