

**AMENDMENT NO. 2 OCTOBER 2014  
TO  
IS 1084 : 2005 TEXTILES — MANILA ROPES —  
SPECIFICATION**

***(Fifth Revision)***

[Page 1, clause 1 (a)] — Substitute ‘8 mm to 128 mm’ for ‘6 mm to 128 mm’.

(Page 1, clause 5, last sentence) — Substitute ‘test piece’ for ‘tests pieces’.

(Page 1, clause 6.1) — Insert ‘(see IS 667)’ at the end of the first sentence.

(Page 1, clause 6.2) — Insert the following new Note under the clause:

‘NOTE — The yarn count is given for guidance only.’

(Page 2, clause 6.6) — Substitute the following for the existing clause:

**‘6.6 Rot-Proofing Treatment**

If so ordered, ropes shall be rot-proofed by the application of zinc or copper based rot-proofing agent in appropriate quantity as agreed to protect the rope from fungus and microbial attack. The rot-proofing agent may be applied at the dressing stage for uniform penetration in the rope. Ropes which have been so treated shall otherwise comply, in all respects with the requirements of this standard. When Zn or Copper are extracted in accordance with IS 3522 (Part 1), it shall be minimum 0.5 percent and 0.2 percent respectively.’

(Page 2, clause 7.1, para 4, sentence 1) — Substitute the following for the existing:

‘Ropes are liable to wear and tear and can be weakened by various agencies like chemicals, heat, light, wind, weather etc, therefore regular inspection is necessary to ensure that the rope is still serviceable for the particular use.’

(Page 2, clause 7.1, para 4, sentence 2) — Substitute ‘Stretching’ for ‘Starching’.

## **Amendment No. 2 to IS 1084 : 2005**

(Page 2, clause **8.3**, Note) — Substitute the following for the existing note:

‘NOTE — Any coil which has been shortened by cutting from it, the necessary test sample shall be accepted at its original length and mass, provided that the test sample complies with the specified requirements.’

(Page 3, clause **13**, heading) — Substitute ‘CONFORMITY’ for ‘CONFOR-MITY’.

(Page 3, clause **13.5** (a)] — Substitute ‘specified/declared length’ for ‘specified declared length’.

(Page 4, Table 1) — Delete ‘Diameter — 6 mm and the requirements thereof’.

(Page 7, Annex A) — Insert ‘IS 667 : 1981 Methods for identification of textile fibres (first revision)’ at appropriate place.