

AMENDMENT NO. 1 NOVEMBER 2005
TO
IS 1239 (PART 1) : 2004 STEEL TUBES, TUBULARS
AND OTHER WROUGHT STEEL FITTINGS —
SPECIFICATION

PART 1 STEEL TUBES

(Sixth Revision)

(Page 1, clause 3.3) — Substitute the following for the existing

‘The ends of the tubes shall be finished clean.’

(Page 2, clause 6.3) — Substitute the following for the existing clause

‘Steel tubes shall be manufactured through one of the following processes.

- a) Hot-finished seamless (HFS),
- b) Cold-finished seamless (CDS),
- c) Hot-finished welded (HFW), and
- d) Electric resistance welded or high frequency induction welded (ERW or HFIW)

NOTE — Tubes made by manual welding are not covered by this specification ’

(Page 3, clause 9.1, Note) — Substitute ‘10 tonnes lot’ for ‘15 tonnes lot’

(Page 5, clause 13.1.1, lines 2 and 3) — Substitute the following for the existing

‘Hydrostatic test shall be carried out at a pressure of 5 MPa and the same maintained for atleast 3 seconds and shall not show any leakage in the pipe.’

(Page 6, clause 17.4) — Substitute the following for the existing clause

‘Tubes having random length 4 to 7 metres shall have two 75 mm bands one near each end Tubes having exact length and approximate length as prescribed in clauses 11.2 and 11.3 shall have one 75 mm band.’

(MTD 19)