



AMENDMENT NO. 2 MARCH 1983
TO
IS : 963-1958 SPECIFICATION FOR
CHROME-MOLYBDENUM STEEL BARS AND
RODS FOR AIRCRAFT PURPOSES

Alteration

(*Page 5, clause 6.1*) — Substitute the following for the existing clause:

‘6.1 The analysis of steel shall be as given below. The analysis of steel shall be carried out either by the method specified in IS : 228* and its relevant parts or any other established instrumental/chemical method. In case of dispute the procedure given in IS : 228* and its relevant parts shall be referee method. However, where the method is not given in IS : 228* and its relevant parts, the referee method shall be as agreed to between the purchaser and the manufacturer.

<i>Constituent</i>	<i>Percent</i>
Carbon	0.26 to 0.35
Manganese	0.40 to 0.60
Phosphorus, <i>Max</i>	0.040
Sulphur, <i>Max</i>	0.040
Silicon	0.20 to 0.35
Chromium	0.80 to 1.10
Molybdenum	0.15 to 0.25
Nickel (residual), <i>Max</i>	0.25 ’

Addenda

(*Page 5, clause 6.2*) — Add the following foot-note after 6.2:

‘ *Methods for chemical analysis of steels. ’