

AMENDMENT NO. 1 JANUARY 1989
TO
IS : 980 - 1980 METHOD FOR DETERMINATION
OF COLOUR FASTNESS OF TEXTILE
MATERIALS TO STOVING
(*First Revision*)

(*Clause 4.4, line 1*) — Substitute 'Fabrics' for 'Fibres'.

(*Clause 4.4, line 3*) — Insert '(see also Appendix A of IS : 1025 - 1982§)' at the end.

(*Page 4, foot-notes*) — Insert the following foot-note:
'§General principles of testing textile for colour fastness tests.'

(*Clause 5.2*) — Substitute the following for the existing clause-
'5.2 Soap Solution — The solution shall contain 5 g of soap per litre. The soap shall conform to the requirement given below, with moisture regain not more than 5 percent. The soap shall be free from optical brightening agents:

<i>Sl No.</i>	<i>Characteristic</i>	<i>Requirement</i>
i)	Free alkali calculated as Na_2CO_3 , <i>Max</i>	0.3 percent
ii)	Free alkali calculated as NaOH, <i>Max</i> ,	0.1 percent
iii)	Combined fatty acids calculated as Na salts, <i>Min</i>	85 percent
iv)	Titre of mixed fatty acids prepared from the soap, <i>Max</i>	39°C
v)	Iodine value of fatty acids, <i>Max</i>	50

(*Page 5, foot-note marked with '*' mark*) — Delete.

(*Clause 7.5, line 2*) — Substitute 'IS : 768 - 1982*' for 'IS : 768 - 1956*'.
(*Clause 7.5, line 4*) — Substitute 'IS : 769 - 1982†' for 'IS : 769 - 1956†'.

(*Clause 7.5, Note*) — Substitute 'NOTE 1' for the existing NOTE and insert 'NOTE 2' after 'NOTE 1' as follows:

'NOTE 2 — In cases of doubt in the colour fastness ratings as assessed by an observer, the assessment should be done by at least three observers and the over-all average rating should be reported.'

(*Page 6, foot-notes*) — Substitute the following for the existing foot-notes:

'*Method for evaluating change in colour (*first revision*).

†Method for evaluating staining (*first revision*).'

(TDC 5)