

AMENDMENT NO. 1 APRIL 2007
TO
IS 9524 : 1980 RECOMMENDED PROCEDURE FOR
REPAIR WELDING OF STEEL COMPONENTS
BY ALUMINO-THERMIC PROCESS

(Page 3, clause 0.3, last line & clause 0.4, line 6) — Substitute 'T19-1994' for 'T19-65'.

(Page 4, clause 4.2, line 2) — Substitute 'Scavenger' for 'scavenger'.

(Page 5, clause 4.3.1, line 2) — Incorporate the following in between the words 'chips' and 'to':

'to reduce the temperature of super heated molten steel to about 2 100°C.'

(Page 5, clause 4.4, line 6) — Substitute '0.015 and 0.65' for '0.30 and 0.70'.

(Page 5, clause 4.4, line 7) — Substitute '0.65' for '0.70'.

(Page 5, clause 4.4, line 8) — Substitute '0.15' for '0.30'.

(Page 12, Table 2, Title) — Add the word 'MIXTURE' in between the words 'THERMIT' and 'REFERRED'.

(Page 14, clause 8.1) — Add the following at the end of the clause:

'For preheating of the job the following method may be adopted. At present there are three different systems:

- i) Use of air-petrol mixture through drum vaporizer,**
- ii) Use of compressed air-petrol mixture through burner, and**
- iii) Use of oxygen and LPG gas mixture through special type of preheating torch.'**

(Page 15, clause 9.2, first sentence) — Substitute the following for the existing:

'The reaction shall be started by a suitable ignition method such as insertion of ignition device (sparkler) in the thermit mixture.'

Amend No. 1 to IS 9524 : 1980

(Page 15, clause 12.1) — Substitute the following for the existing clause:

‘Wherever possible the welds should be subjected to suitably qualified non-destructive methods to ensure freedom from defects. The acceptance limit for the flaws shall be mutually agreed between the user and manufacturers.’

(Page 15, clause 13.1, second line) — Incorporate the following in between the words ‘be’ and ‘adequately’:

‘educated at least up to Secondary School (high school/matriculation pass) or having ITI certificate or equivalent and’

(MTD 12)

Reprography Unit, BIS, New Delhi, India