

**AMENDMENT NO. 3 MARCH 2002
TO
IS 9537 (PART 2) : 1981 SPECIFICATION FOR
CONDUITS FOR ELECTRICAL WIRING
PART 2 RIGID STEEL CONDUITS**

(*Title of the standard*) — Substitute the word 'WIRING' with 'INSTALLATIONS' and wherever it appears in the standard.

(*Page 9, clause 7.3.2*) — Insert the following note at the end:

'NOTE — In no case, the measurement of wall thickness shall be taken at the welded portion '

(*Page 9, clause 7.3.2*) — Insert the following new clause after 7.3.2:

7.3.3 Uniformity of the Wall Thickness — In case of doubt with regard to the uniformity of the wall thickness of conduits, three samples, each taken from different lengths, shall be cut along a plane perpendicular to the axis. The wall thickness at each cut edge shall be measured at four places as far as possible equally spaced around the circumference, one of the measurement being made at the thinnest place. In no case shall the difference between the values measured and the average of the twelve values obtained for the three samples exceed 0.1 mm $\pm$ 10 percent of the average value.'

(ETD 14)