

AMENDMENT NO. 1 MARCH 2002
TO
IS 9537(PART3) : 1983 SPECIFICATION FOR
CONDUITS FOR ELECTRICAL INSTALLATIONS
PART 3 RIGID PLAIN CONDUITS OF INSULATING MATERIALS

(Page 4, clause 1.1) — Substitute the following for the existing clause:

'This standard (Part 3) specifies requirements and method of tests for circular rigid non-flame propagating and non-threadables plain ended and socket ended conduits of insulating materials.

NOTE — In the case of socket ended conduits, the socket portion shall be integral with the conduit length at one end only.

(Page 5, Table 1) — Insert the following new clause after Table 1 and renumber the existing clause 7.1.1 as clause 7.1.2:

7.1.1 The dimensions of the socket end shall be as given in Table 2.

Table 2 Dimensions of Socket End
All dimensions in millimetres.

Nominal size	Outside Diameter (Max)	Inside Diameter	Length of Socket End (Min)
(1)	(2)	(3)	(4)
16	20.1	16.1 } +0.2	40
20	24.5	20.1 } 0	40
25	29.8	25.1 } +0.3	40
32	37.8	32.1 } 0	50
40	46.1	40.1 } +0.4	60
50	57.3	50.1 } 0	60
63	69.6	63.1 } ±0.5	60
		0	

(Page 7, clause 7.3) — Substitute the following for the existing clause:

'7.3 The preferred length of a conduit shall be 3 m. Other lengths are also permitted with agreement between the manufacturer and the purchaser.'

(Pages 14 and 15, Appendix A) — Substitute 'Table 3' for 'Table 2' wherever it appears.

(ETD 14)