

**AMENDMENT NO. 5 DECEMBER 2000
TO
IS 9562 : 1980 SPECIFICATION FOR NON-METAL
HELMET FOR POLICE FORCE**

(Page 12, *APPENDIX F*) — Substitute the following for the existing:

**APPENDIX F
(Clause 9.6)**

METHOD OF TESTING FLAMMABILITY RESISTANCE

F-1 SAMPLES

F-1.1 The samples for testing shall be selected as given in 8.1.

F-2 BURNER

F-2.1 Burner shall be operated with the valve so as to get a flame height of 150 mm. Satisfactory operation of burner shall be checked by inserting in the flame, the bare copper wire of 0.71 mm diameter having a free length of not less than 100 mm in position normally occupied by low edge of the test piece, that is, 50 mm above the burner and reaching farther edge of the flame. The wire should not take more than 6 seconds to melt.

F-3 PROCEDURE

F-3.1 The helmet shall be supported, crown uppermost, on a head form (*see* IS 7692).

A burner conforming to the requirements given in F-2 is to be brought into contact with outer surface of the helmet with the flame at right angles at a point of 12 cm below the crown, measured externally, whilst it is rotated steadily through one complete revolution at a speed of 2 rev/min.

(CED 22)