

AMENDMENT NO. 1 JULY 1988

TO

**IS:9704-1980 METHODS OF TESTS FOR LINOLEUM
SHEETS AND TILES**

(Page 9, clause 8.4) - Substitute the following
for the existing clause:

'8.4 Procedure - The test pieces shall be subjected to three cycles of alternate heating in the air oven at $70 \pm 1^{\circ}\text{C}$ for 24 hours and then cooling to a temperature of $27 \pm 2^{\circ}\text{C}$ for 24 hours. The test pieces shall then be subjected to various tests as specified.

(BDC 5)

Printed at Dee Kay Printers, New Delhi-110015, India.