

**AMENDMENT NO. 2 JUNE 2003
TO
IS 9704 : 1990 METHOD OF TEST FOR LINOLEUM
SHEETS AND TILES**

(Page 3, clause 1.1) — Delete:

<i>'Test</i>	<i>Clause Ref</i>
g) Ageing	8'

[Page 3, clause 1.1(h)] — Substitute '8' for '9'.

(Page 8, clause 6.5, lines 3 and 4) — Substitute "2.0" for '1.6' and '2.5' for '2.0'.

(Page 9, clause 8) — Delete.

(Page 9, clause 9) — Substitute the following for the existing clause:

'8 COLOUR FASTNESS TO DAY LIGHT

8.1 Object

To determine the colour fastness to daylight of linoleum sheet and tiles.

8.2 Test Specimen

Test pieces measuring 50 × 25 mm shall be cut from each sample piece.

8.3 Apparatus

8.3.1 Exposure Rack — as described in IS 686 : 1985 'Method of determination of colour fastness of textiles materials to daylighting (*first revision*).

8.3.2 Geometric Grey Scale — For assessing the change of colour (*see* IS 768 : 1956 'Method of evaluating change of colour'.

8.3.3 Standard Pattern — A set of standard pattern of Blue Wool Cloth as prescribed in IS 686 : 1985 'Method of determination of colour fastness of textiles materials to daylighting (*first revision*).

Amend No. 2 to IS 9704 : 1990

8.4 Procedure

8.4.1 Before commencing the test procedure, expose the reference sample in full, together with blue wool standard cloth reference 2 unit a contrast is produced on blue wool standard cloth reference 2 equal to the contrast illustrated by Grey Scale 3. This step is necessary to remove the stove yellowing of linoleum before the stable colouration is achieved.

8.4.2 The test pieces exposed as described in 8.4.1 and the standards blue wool cloth standard shall be exposed to daylight and tested as per procedure laid down in IS 686. The test pieces and the standards shall be observed at suitable intervals until standard pattern for light fastness rating No. 5 show fading equivalent to grade 4 on Geometric Grey Scale. The exposed and unexposed portions of the test specimens shall be compared with the standard pattern No. 5.

8.5 Report —The report shall state:

Any change in exposed and unexposed portions of the test pieces with the standard pattern No. 5 shall be reported.

(CED 5)