

AMENDMENT NO. 1 MARCH 2011
TO
IS 14343 : 1996 CHOICE OF GROUTING MATERIALS FOR ALLUVIAL
GROUTING — GUIDELINES

(Page 1, clause 3, line 6) — Substitute ‘non-particulate (see 6)’ for ‘chemical (see 6)’.

(Page 2, Table 1) — Substitute the following for the existing:

PERMEABILITY	GROUTABILITY
K = less than 10 ⁻⁶ cm/sec	UngROUTable
K = 10 ⁻⁶ cm/sec to less than 10 ⁻⁵ cm/sec	Groutable with difficulty by grouts having viscosity lower than 5 cP and ungroutable at higher viscosities
K = 10 ⁻⁵ cm/sec to less than 10 ⁻³ cm/sec	Groutable with low viscosity grouts but with difficulty when viscosity is greater than 10 cP
K = 10 ⁻³ cm/sec to less than 10 ⁻¹ cm/sec	Groutable with all commonly used chemical grouts
K = 10 ⁻¹ cm/sec or more	Groutable with suspended solids grout or chemical grout with filler

(Page 4, Table 2, col heading 3) — Substitute ‘**Optimum Dosage** (percentage by weight of cement)’ for ‘**Optimum Dosage** (percentage by weight)’

(Page 5, clause 6.3, para 5, line 5) — Substitute ‘A newly made silica gel will, upon standing, exude water and shrink and this process is called syneresis.’ for ‘A newly made silica gel will, upon standing, exude water and shrink.’

(Page 6, clause 6.4.2, Title) — Substitute ‘*Lignosulfonate Grouts*’ for ‘*Lingnosulfonate Grouts*’.

(Page 7, Fig. 2C) — Delete.

(Page 8, Fig. 2D) — Delete.

(Page 8, clause 6.6.2.2, line 4) — Substitute ‘Materials which are highly sensitive, cause difficulty in handling. Prior knowledge of sensitivity of chemical grout to particular pH is useful. If not, trial experiments should be conducted.’ for ‘Materials which are highly sensitive cause difficulty in handling.’