

AMENDMENT NO. 1 JUNE 2011
TO
IS 14402 : 1996 GLASS FIBRE REINFORCED PLASTICS (GRP) PIPES, JOINTS
AND FITTINGS FOR USE FOR SEWERAGE, INDUSTRIAL WASTE AND
WATER (OTHER THAN POTABLE) — SPECIFICATION

(Page 2, Table 1) — Insert the following at appropriate places in ascending order in the table:

Nominal Diameter, DN	Inside Diameter Range, ID		Tolerances on Declared ID
	<i>Min</i>	<i>Max</i>	
1 300	1 295	1 320	±5
1 500	1 495	1 520	±5

(Page 3, Table 2) — Insert the following at appropriate places in ascending order in the table:

Nominal Diameter, DN	Outside Diameter Range, OD	Tolerances on Declared OD
1 300	1 330	±5
1 500	1 534	±5

(Page 7, Table 6) — Insert the following at appropriate places in ascending order in the table:

Nominal Diameter	Beam Load	Minimum Longitudinal Tensile Strength in kN/m of Circumference, for Pressure Class				
		PN 3	PN 6	PN 9	PN 12	PN 15
DN	P					
1 300	—	152	226	345	393	468
1 500	—	175	265	397	454	540

(Page 7, Table 7) — Insert the following at appropriate places in ascending order in the table:

Nominal Diameter	Minimum Hoop Tensile Strength of Pipe Wall in kN/m Width of Circumference for Pressure Class				
mm	PN 3	PN 6	PN 9	PN 12	PN 15
1 300	790	1 580	2 369	3 159	3 949
1 500	911	1 823	2 734	3 645	4 556

Amend No. 1 to IS 14402 : 1996

(Page 13, clause **E-5.3**) — Substitute the following for the existing:

‘Load the test piece by separating the mounts at a rate not exceeding 2.5 mm/min and record the maximum force resisted by the test piece.’

(CED 50)