

AMENDMENT NO. 1

Page 4

5.1 Solid conductor

Delete "plain" from the first sentence.

5.4 Tear propagation of the locating groove

At the end of the first paragraph, change "20 N" to "10 N".

5.5 Resistance to perforation

Replace the title and text of this sub-clause by the following:

5.5 Insulation material hardness

The insulation shall be of a hardness which will permit a satisfactory connection by the ID method of termination. The hardness of the material shall be determined on a plaque moulded from granules and measured in accordance with ISO 868: Plastics and ebonite - Determination of indentation hardness by means of a durometer (Shore hardness).

The maximum hardness after 15 s shall not exceed 89 by the type A Shore durometer method. A measurement tolerance of ± 3 shall be allowed.

NOTE - Consideration may be given to use harder PVC with a limited number of conductors (for example hardness up to 100 with a limited number of 20 conductors).

Page 8

Appendix E – Thermal shock

In the first sentence of this appendix, replace "to five" by "within 1 h to a test consisting of five".

Page 9

Appendix K – Resistance to perforation

Delete this appendix.