

**AMENDMENT NO. 1 FEBRUARY 2005
TO
IS 14588 : 1999 BOMBOO MAT-VENEER COMPOSITE
FOR GENERAL PURPOSES — SPECIFICATION**

(Page 2, clause 6.2) — Substitute the following for the existing clause:

‘6.2 The bamboo mat-veneer composites shall be of following dimensions:

2 440 mm × 1 220 mm 1 840 mm × 1 220 mm
2 140 mm × 1 220 mm 1 840 mm × 920 mm
2 140 mm × 920 mm

(Page 2, clause 6.3) — Add the following Note below clause 6.3:

‘NOTE — Any other dimensions (length, width and thickness) as agreed to between the manufacturer and the purchaser may also be used.’

(Page 2, clause 6.4) — Add the following Note at the end of the clause:

NOTE — Edge straightness and squareness shall be tested as per Annex C.

(Page 3, clause 9.5.3) — Add the following new clause at the end:

9.6 Modulus of Rupture (MOR) and Modulus of Elasticity (MOE)

Three test specimens for MOR and MOE from each sample may be drawn as specified in IS 1734 (Part 11) : 1983. Modulus of rupture and modulus of elasticity shall be determined for each test specimen in accordance with the method prescribed in IS 1734 (Part 11) and the average and minimum individual values shall not be less than the values given in Table 1.

Table 1 Average and Minimum Individual Values of Modulus of Elasticity (MOE) and Modulus of Rupture MOR)

	MOE (N/mm ²)	MOR (N/mm ²)
Average	3 000	30
Minimum Individual	2 700	27

