

AMENDMENT NO. 1 APRIL 2024
TO
IS 14606 : 2022 IRRIGATION EQUIPMENT — GRANULATED
MEDIA FILTERS — SPECIFICATION
(First Revision)

(Page 1, clause 2) — Insert the following:

<i>IS No.</i>	<i>Title</i>
4984 : 2016	Polyethylene pipes for water supply — Specification (<i>fifth revision</i>)
4985 : 2021	Unplasticized PVC pipes for water supplies — Specification (<i>fourth revision</i>)
15801 : 2008	Polypropylene-random copolymer pipes for hot and cold water supplies — Specification'

(Page 2, clause 4.4.1) — Substitute the following for the existing:

‘Relatively slow flow, less than 50 m³/h-m².’

(Page 4, clause 6.2.3.1) — Substitute the following for the existing:

‘6.2.3.1 Filters with plastic filter housing shall be tested either as per the test method given in 6.2.2 or alternatively as per the procedure given in 6.2.3.2.

6.2.3.2 The pressure test shall be performed on an injection-moulded tube specimen made of the same material as the plastic moulded body. The dimensions of the specimen shall be as shown in Fig. 1. The wall thickness of the test sample shall not be less than that fitting a PN6 pipe and not greater than for a PN12.5 pipe for the same diameter as per IS 4984, 4985 and 15801. The specimen shall be tested in accordance with Annex A and shall meet the strength requirements specified in Table 2. The specimen tested shall not suffer fracture or other damage.

NOTES

1 This test shall be carried out either once in a year or whenever a change is made in the polymer, composition or colour or master batch or new size in order to establish the suitability and the performance capability of the filter.

2 Manufacturer shall declare the raw material used for manufacturing plastic filter housing and material test report should also be available with the manufacturer as a declaration for conformity of the raw material.’

(Page 4, Table 2) — Substitute the following for the existing:

Table 2 Test Conditions and Requirements
(Clause 6.2.3.2)

Sl. No.	Material	Temperature	Circumferential Stress	Minimum Duration	Reference Indian Standards
(1)	(2)	°C	N/mm ²	h	
(1)	(2)	(3)	(4)	(5)	
i)	PVC-U	60	10	1 000	IS 4985
ii)	PE 63	80	3.5 (3.2)	165 (1 000)	IS 4984
iii)	PE 80	80	4.5 (4.0)	165 (1 000)	IS 4984
iv)	PE 100	80	5.4 (5.0)	165 (1 000)	IS 4984
v)	PP (Glass reinforced)	95	3.5	1 000	IS 15801
vi)	POM	60	10	1 000	—
vii)	ABS	70	4	1 000	—
viii)	PA6 (GF reinforced)	70	4	1 000	—

Price Group 1

(Page 5, clause 9) — Insert the following at the end:

‘NOTE — Back flushing may be done either manually or automatically. Manufacturer is required to provide either manual back flushing or automatic back flushing mechanism with the filter for conducting the above test. Testing for controller mechanism of automatic back flushing is given in 10.’

(Page 6, clause 10.1, para 1) — Substitute the following for the existing:

‘Initiation of individual backwash operations for a filter system shall be as per the manufacturer’s criteria with respect to any of the following controller mechanism:

- a) Specified timing (for example, 3 h) between backwash events; or
- b) Achieving a specified pressure drop across the filter system; or
- c) Both timing and pressure drop; or
- d) By volume of filtered water.’

(Page 9, clause 16.2, last sentence) — Substitute the following for the existing:

‘For the test specified in 6.2 (excluding 6.2.3.2), 8, 9.1, 9.2 and 10.2 the shipment or manufacturing lot complies with this standard if number of defective specimens found in the test does not exceed the acceptance number specified in IS 2500 (Part 1).’

(Page 10, Annex A) — Substitute clause ‘6.2.3.2’ for ‘6.2.3.1’ wherever referred.

(Page 12, clause A-4.4) — Substitute the following for the existing formula:

$$p = \frac{2(10.2\sigma)}{[SDR] - 1}$$