

**AMENDMENT NO. 1 JULY 2007
TO
IS 14661 : 1999 TOILET PAPER — SPECIFICATION**

(Page 2, clause 5.6) — Substitute the following for the existing:

'5.6 The paper shall also comply with the requirements given in Table 1.'

(Page 2, Table 1) — Substitute the following table for the existing:

Table 1 Requirements for Toilet Paper
(Clause 5.6)

Sl No.	Characteristic	Requirement	Method of Test, Ref to		
			CI No. in IS 1060 (Part 1)	CI No. in IS 1060 (Part 2)	Annex
(1)	(2)	(3)	(4)	(5)	(6)
i)	Tensile strength, dry cross section, 50 mm gauge length, N/m, <i>Mm</i>	44	12	-	-
ii)	Absorption time, 0.01 ml distilled water, s, <i>Max</i>	25	-	-	Annex B
iii)	Brightness, average both sides, percent, <i>Min</i>	75	—	13	-

(Page 4, Annex A) — Insert the following Annex at the end of Annex A:

ANNEX B
[Table 1, Sl No. (ii)]

DETERMINATION OF ABSORPTION TIME

B-1 APPARATUS AND MATERIALS

B-1.1 Volume measuring device, syringe, capable of measuring 0.01 ml volume.

B-1.2 Specimen support, a piece of metal or other non-absorbent material about 100 × 100 mm, with a central hole of approximately 40 mm diameter.

B-1.3 Light source, to reflect light from the surface of unabsorbed water on the specimen, situated far enough away so that its heat will not influence the absorption time.

NOTE - A 1.5-V flashlight bulb, shaded from the eyes, placed about 200 mm above and to the rear of the support and operated by a 'D' cell battery or a bell transformer, makes a very good light source for this purpose.

B-1.4 Timer, stopwatch or electric timer readable to 0.2 s or better.

B-1.5 Distilled water.

B-2 SAMPLING AND TEST SPECIMENS

B-2.1 Obtain a representative sample of the paper. From each sample cut 10 specimens, each approximately 100 × 100 mm.

B-3 PROCEDURE

B-3.1 Condition and test the specimens in the conditioning and testing atmosphere temperature 27 ± 1°C and relative humidity 65 ± 2 percent for at least one hour prior to testing.

Amend No. 1 to IS 14661 : 1999

B-3.2 Place a test specimen on the horizontal support which has a clear space of at least 10 mm beneath it. Do not stretch or in any way distort the test specimen, as this may change the results from the test. Fill the syringe with distilled water at $27 \pm 1^\circ\text{C}$.

B-3.2.1 Hold the tip vertical of syringe, express a volume 0.01 ml, and apply the volume directly to the specimen.

B-3.3 Start the timer as soon as the water contacts the specimen and measure the time for the water to be completely absorbed to the nearest 0.2 s or better, as indicated visually by the disappearance specular reflection of light (or the moment of disappearance of the glossy or shiny area from the wet spot).

B-3.4 Conduct the test where neither heat from the light nor a strong current of air might influence the result.

B-3.5 Repeat the procedure on the other nine test specimens.

B-4 REPORT

B-4.1 Report the volume used, and the average absorption time in seconds, to the nearest second if over 10 s, or to the nearest 0.2 s if less than 10 s.