

AMENDMENT NO. 1 OCTOBER 2009
TO
IS 14713 : 1999 SYNTHETIC (FUSED) MULLITE AND ALUMINA GRAINS FOR
REFRACTORY INDUSTRY — SPECIFICATION

(Page 2, Table 2) — Substitute the following for the existing table:

Table 2 Physical Properties of Fused Mullite and Fused Alumina Grains

Sl No.	Grade Designation	Grain Density g/cc (<i>Min</i>)	Apparent Porosity Percent (<i>Max</i>)
(1)	(2)	(3)	(4)
i)	MF	3.00	1.0
ii)	ABF	3.80	1.0
iii)	AWF	3.65	1.0