

**AMENDMENT NO. 1 APRIL 2004
TO**

**IS 14735 : 1999 UNPLASTICIZED POLYVINYL
CHLORIDE (UPVC) INJECTION MOULDED FITTINGS
FOR SOIL AND WASTE DISCHARGE SYSTEM FOR
INSIDE AND OUTSIDE BUILDINGS INCLUDING
VENTILATION AND RAIN WATER SYSTEM —
SPECIFICATION**

(*Foreword*) — Insert following new para at the end of second para:

'In view of overall scenario in India, a minimum 2.5 percent of titanium dioxide is considered necessary to be included in the material composition of UPVC pipes in order to safeguard its quality. Usually 4.5 percent of titanium dioxide was recommended. However, detailed studies carried out in developed countries on weathering behaviour of UPVC pipes had shown that at 2.5 percent titanium dioxide, sufficient opacity and UV absorption is provided. Beyond this percentage of titanium dioxide, no benefit is gained in retention of gloss, colour and mechanical properties such as yield stress and elongation at break.'

(CED 50)