

AMENDMENT NO. 1 FEBRUARY 2026
TO
IS 14756 : 2024 STAINLESS STEEL UTENSILS — SPECIFICATION
(Third Revision)

(Page 1, clause 3.3) — Substitute the following for the existing:

‘If the body of the utensil is made of 3-ply construction, it shall conform to IS 18755 or comply with **6.4** and **6.6**.

NOTES

1 Since the utensil is being tested as per **6.6**, only induction test to be done as per **6.4**.

2 Material composition of 3-ply shall be as per IS 18755.’

(Page 1, clause 3.5) — Substitute the following for the existing:

‘If the utensil is provided with a tempered glass lid, the lid shall conform to the performance requirements as given in IS 2347. The minimum thickness of glass shall be 3.5 mm. If stainless-steel rim is provided on the glass lid, the chemical composition of the material of rim shall be as per IS 5522/grades of IS 5522 as per IS 6911 or IS 15997/grades of IS 15997 as per IS 6911. The minimum thickness of the rim shall be 0.25 mm.

NOTE — Only chemical composition of material of the rim needs to be complied with. Supplier certificate is acceptable.’

(Page 1, clause 3.5) — Insert the following at the end:

‘**3.6** The process of welding for utensils made of grades as per IS 15997 or grade 430 of IS 5522/IS 6911 shall have the following:

- a) The weld shall be finished as per Annex E;
- b) In case of utensils more than 300 mm in size, a weld test piece can be made (test piece shall be of the same material as utensil). The test piece can be of 75 mm (l) × 25 mm (w); and
- c) Welders shall be qualified internally and record of tests done as per Annex C and Annex D shall be maintained (each welder used shall have qualification records). Welder qualification check can be done once in a year.’

‘**3.7** In case of the products made of stainless steel with exterior plastic moulding and plastic lid, the plastic shall be food grade and shall not contain Bisphenol A (BPA). It shall also conform to the requirements of IS 9845.’

(Page 1, clause 4.3) — Substitute the following for the existing:

‘Where specified, the utensil shall be classified as follows:

- a) Domestic; and
- b) Commercial.’

Amendment No. 1 to IS 14756 : 2024

(Page 2, Table 1) — Substitute the following for the existing:

‘Table 1 Minimum Sheet Thickness for Body of Utensil

(Clause 4.2)

Sl No.	Type of Utensil	Minimum Thickness of Sheet, mm	
		Vessel with cladding	Vessel
(1)	(2)	(3)	(4)
i)	Cooking utensil	0.5	0.5
ii)	Serving utensil Type CS	0.5	0.5
iii)	Serving utensil Type S	Not applicable	0.3
iv)	Table utensil	Not applicable	0.3
v)	Storing utensil	Not applicable	0.3

NOTE — For commercial utensils (cooking utensils and serving utensils type CS); the minimum thickness of the sheet shall be ≥ 1 mm. For other types of commercial utensils, the minimum thickness shall be ≥ 0.4 mm. It is mandatory to mark the thickness for both domestic and commercial utensils.’

(Page 2, Table 2) — Substitute the following for the existing:

‘Table 2 Minimum Sheet Thickness for SS Lid of Utensil

(Clause 4.2)

Sl No.	Type of Utensils	Minimum Thickness of Sheet in mm
(1)	(2)	(3)
i)	Cooking utensil	0.3
ii)	Serving utensil Type CS	0.3
iii)	Serving utensil Type S	0.3
iv)	Table utensil	0.3
v)	Storing utensil	0.3

NOTE — The permissible reduction in the thickness of the lid, taking into account the pressing or spinning process, shall not be more than 20 percent.’

(Page 2, clause 4.4) — Substitute the following for the existing:

‘The thickness of aluminium disc/core and protector/cowl for composite bottom utensils shall be as given below:

Sl No.	Composite Bottom — 2-ply and 3-ply	Thickness in mm
(1)	(2)	(3)
i)	Aluminium disc/core	≥ 1.5
ii)	Protector/cowl	≥ 0.4

NOTE — The material thickness for 2-ply and 3-ply composite bottom of stainless-steel utensil can also be as per IS 15960.’

(Page 3, clause 4.5, para 1) — Substitute the following for the existing:

‘The minimum sheet thickness of 3-ply utensil shall be $1.5 \text{ mm} \pm 0.15 \text{ mm}$.’

(Page 3, clause 5.3) — Add following note at the end:

‘NOTE — Only chemical composition of stainless steel needs to be complied with. Supplier certificate is acceptable.’

(Page 4, clause 6.1, line 6) — Substitute the following for the existing:

‘with any one of the following solutions at ambient’

(Page 4, clause 6.7.1) — Add following note at the end:

‘NOTE — Any utensil having an actual capacity equal to or greater than the declared nominal capacity shall be considered compliant with this clause.’

(Page 5, clause 6.7.2) — Substitute the following for the existing:

‘In case the marking or labelling is in terms of diameter, the internal diameter of utensil shall be marked (except for *Tawa*, where the diameter is outer diameter). The dimensions shall be exclusive of the handles. The diameter shall be expressed only in complete or 0.1 cm units. The tolerance on the diameter shall be ± 1.5 mm or ± 2 percent of the diameter, whichever is higher.

NOTE — If the diameter is 39.25 cm, its diameter shall be marked as the nearest complete of 0.1 cm units, the diameter to be marked as 39.2 cm or less (39.1 cm, 39 cm).’

(Page 5, clause 8.1) — Substitute the following for the existing:

‘Each utensil shall have the following details:

- a) Capacity in litre/millilitre or size in cm/mm of utensil;
- b) Thickness of sheet (mm);
- c) Material grade (Lid-SS 304 or SS 304/Al 19000/SS 430, Body-SS 304 or SS304/Al 19000/SS 430);
- d) Manufacturer name or initials or trademark; and
- e) Batch number.

NOTES

1 All utensils shall have ISI mark and CML No. on utensils only. It could be either stamped, embossed, etched or laser marked.

2 Details given in (a), (b), (c), (d) and (e) can be marked on sticker and primary packaging.

3 Details can also be put on primary packaging for lid if sold separately.

4 Details can be put on primary packaging or sticker for small utensils (less than 160 mm diameter).’