

**AMENDMENT NO. 1 JANUARY 2010
TO
IS 14852 : 2000 FLAKY GRAPHITE FOR
REFRACTORY INDUSTRY — SPECIFICATION**

(Page 1, clause 6.2, Table 1) — Substitute the following for the existing table:

Table 1 Chemical Requirement of Graphite for Refractory Industries
(Clause 6.2)

Sl No.	Characteristic	Requirement, Percent by Mass					Method of Test (Ref to Clause in Annex A)
		Gr I	Gr II	Gr III	Gr IV	Gr V	
(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)
i)	Moisture, <i>Max</i>	0.20	0.25	0.50	0.2	0.2	A-2
ii)	Analysis on dry basis:						
	a) Volatile matter, <i>Max</i>	2.00	2.00	2.50	0.8	1.0	A-3
	b) Ash; <i>Max</i>	5.00	7.00	9.50	2.2	5.0	A-4
	Fe ₂ O ₃ , <i>Max</i>	2.00	3.00	4.00	0.4	0.75	A-4.2
	TiO ₂ , <i>Max</i>	1.00	1.50	2.00	Traces	Traces	
	CaO, <i>Max</i>	1.00	1.50	2.00	0.05	0.1	
	SiO ₂ + Al ₂ O ₃ , <i>Max</i>	Balance	Balance	Balance	Balance	Balance	
	Alkalis, <i>Max</i>	1.50	2.00	3.00	0.03	0.05	
	c) Fixed Carbon, <i>Min</i>	93.00	90.00	88.00	97	94	A-5
iii)	Sulphur, <i>Max</i>	0.25	0.25	0.50	Traces	Traces	A-6

(MTD 13)

Reprography Unit, BIS, New Delhi, India