

## AMENDMENT NO. 3 FEBRUARY 2021

TO

### IS 14887 : 2014 TEXTILES — HIGH DENSITY POLYETHYLENE ( HDPE ) / POLYPROPYLENE ( PP ) WOVEN SACKS FOR PACKAGING OF 50 KG FOOD GRAINS — SPECIFICATION

( *First Revision* )

(Page 1, clause 3.2) — Substitute the following for the existing clause:

#### **‘3.2 Fabric**

The fabric used in the manufacture of HDPE/PP woven sacks shall be woven as a tube on circular looms from HDPE/PP tapes having width of 2.5 mm (tolerance of  $\pm 5$  percent) conforming to IS 6192 and IS 11197 respectively, and linear density of 111 tex (1 000 denier). The woven fabric shall be of mesh  $12 \times 12$  and 105 g/m<sup>2</sup> weight (with a tolerance of  $\pm 3$  percent on weight). The denier of HDPE/PP tape used in the manufacture of woven fabric/sacks shall be subjected to the following tolerances:

- a)  $\pm 10$  percent on individual value, and
- b)  $\pm 5$  percent on average.

The construction particulars of fabric shall be as given in Table 1. Also the construction particulars specified are expected to ensure aeration of foodgrains. The fabric shall be woven with anti-slip pattern (as given in Fig. 1) to avoid oozing of grains out of the sacks and for better stackability.’

(Page 2, Note 3 under Table 1) — Substitute the following for the existing note:

‘3 The mass of sack is based on fabrics weighing 105 g/m<sup>2</sup>.’