

AMENDMENT NO. 1 APRIL 2005
TO
IS 14951 : 2001 FIRE EXTINGUISHER —
135 LITRES CAPACITY MECHANICAL FOAM TYPE —
SPECIFICATION

[Page 3, clause 5, Table 1, Sl No. (x), col 4] — Substitute 'IS 7285' for the existing matter.

(Page 3, clause 9.1) — Substitute the following for the existing:

'9.1 All internal and external surfaces of the body shall be completely epoxy powder coated to minimum 0.050 mm thickness. The thickness of the coating shall be measured as given in IS 3203. The internal surface of the body shall be plastic/rubber coated and lining shall be of a minimum thickness of 0.5 mm as an alternative to powder coating.

9.1.1 Test for Adhesion of Pastic Lining (Type Test) — Subject the unfilled extinguisher to a pressure 15 kgf/cm² and store for $120 + \frac{4}{-0}$ h at $27 \pm 5^{\circ}\text{C}$.

Release the pressure and examine the extinguisher internally for cracking, separation from the wall of the body or lifting of the lining, and bubbles between the lining and the body.'

(Page 3, clause 9.1.1) — Renumber '9.1.1' as '9.2' and delete 'to lead-tin alloy' from last line.

(Page 3, clause 10.1) — Insert 'or Post Office Red' after 'fire red' and 'or No. 538' after 'No. 536'.

(Page 4, clause 11.1, line 5) — Substitute '1.25 m' for '12.5 m'.

(CED 22)

Reprography Unit, BIS, New Delhi, India