

**AMENDMENT NO. 1 AUGUST 2007
TO
IS 14959 (PART 2) : 2001 DETERMINATION OF WATER
SOLUBLE AND ACID SOLUBLE CHLORIDES IN
MORTAR AND CONCRETE — METHOD OF TEST**

PART 2 HARDENED MORTAR AND CONCRETE

(Page 1, clause 4.1.6, line 1) — Insert 'dried at 160°C and cooled in a desiccator' after 'silver nitrate'.

(Page 2, clause 4.1.6, last line) — Add at the end 'and record the exact normality of the silver nitrate solution'.

(Page 2, clause 4.1.7, first line) — Substitute '1.52 g' for '1.7 g'.

(Page 2, clause 4.1.7, last line) — Add at the end 'or record the exact normality'.

(Page 2, clause 4.1.7) — Add the following note at the end:

'NOTE — Sometimes it is difficult to make exactly 0.02 N solution if the standard normality of the solution is less'.

(Page 2, clause 4.3.1.2, line 3) — Insert 'or more' after '25 ml' and substitute '0.02 N' for '0.2 N'.

(Page 2, clause 4.3.2.2, line 2) — Delete 'Add 5 ml of 6 N nitric acid.'

(Page 2, clause 4.3.2.2, line 3) — Substitute 'or more of 0.02 N' for 'of 0.2N'.

(Page 2, clause 4.4, lines 3 to 7) — Substitute the following for the existing formula:

$$\text{Chloride, percent} = \frac{2 \times 0.709 (X-Y)}{m}$$

where

X = volume of 0.02 N silver nitrate added, in ml;

Y = volume of 0.02 N ammonium thiocyanate consumed; and

m = mass of concrete sample taken for test, in g.

(CED 2)

Reprography Unit, BIS, New Delhi, India