

AMENDMENT NO. 2 SEPTEMBER 2017
TO
IS 14968 : 2015 TEXTILES — HIGH DENSITY
POLYETHYLENE (HDPE)/POLYPROPYLENE (PP)
WOVEN SACKS FOR PACKAGING
50 kg/25 kg SUGAR — SPECIFICATION

(First Revision)

[Page 2, Table 1, Sl No. (i)] — Delete.

[Page 2, Table 1, Sl No. (ii), (viii) and (ix)] — Substitute the following for the existing:

Sl No.	Characteristic	Requirement		Tolerance	Method of Test, Ref to
		Type I	Type II		
(1)	(2)	(3)	(4)	(5)	(6)
ii)	Dimensions (see Notes 1 and 2):				Annex B
	a) Inside length, mm	900	630	+ 20/-10	
	b) Inside width, mm	590	480	+ 20/- 10	
viii)	Elongation at break of fabric, (Ravelled strip method), percent :				IS 1969 (Part 1)
	a) Lengthwise	15 to 25	15 to 25	—	
	b) Widthwise	15 to 25	15 to 25	—	
ix)	Breaking strength of fabric after exposure to UV radiation and weathering, Min	50 percent of original value		—	Annex C

(Page 5, clause **D-1**, lines 4 and 5) — Substitute ‘590°C’ for ‘550°C’.

(Page 5, clause **D-2.5**, line 2) — Substitute ‘590°C’ for ‘550°C’.

(Page 6, clause **D-4.1**, line 1) — Substitute ‘590°C’ for ‘550°C’.

(Page 6, clause **D-4.5**, line 2) — Substitute ‘590°C’ for ‘550°C’.