

AMENDMENT NO. 3 JULY 2021

TO

IS 14968 : 2015 TEXTILES — HIGH DENSITY POLYETHYLENE (HDPE) / POLYPROPYLENE (PP) WOVEN SACKS FOR PACKAGING 50 kg/25 kg SUGAR — SPECIFICATION

(*First Revision*)

(Page 1, *clause 4.2*) — Substitute the following for the existing clause:

‘4.2 Fabric

The fabric used in the manufacture of HDPE/PP woven sacks shall be woven as a tube on circular looms from HDPE/PP tapes having width of 2.5 mm (tolerance of ± 5 percent) conforming to IS 6192 and IS 11197 respectively and linear density of 111 tex (1 000 denier) for Type 1 sacks and 94 tex (850 denier) for Type 2 sacks. The woven fabric shall be of mesh 12×12 and 105 g/m^2 weight (with a tolerance of ± 3 percent on weight) for Type 1 sacks and of mesh 11×11 and 82 g/m^2 weight (with a tolerance of ± 3 percent on weight) for Type 2 sacks. The denier of HDPE/PP tape used in the manufacture of woven fabric/sacks shall be subjected to the following tolerances:

- a) ± 10 percent on individual value, and
- b) ± 5 percent on average.

The construction particulars of fabric shall be as given in Table 1.’

(Page 1, *clause 4.4, sentence 2*) — Substitute the following for the existing sentence:

‘The thickness of liner, when tested in accordance with Annex B of IS 2508, shall be minimum $50 \mu\text{m}$.’

(Page 2, *Table 1, Note 3*) — Substitute the following for the existing note:

‘3 The mass of sack is based on fabrics weighing 105 g/m^2 and 82 g/m^2 for Type 1 and Type 2 sacks respectively.’

(Page 4, Annex A) — Insert the following new reference at an appropriate place:

<i>IS No.</i>	<i>Title</i>
2508 : 2016	Polyethylene films and sheets — Specification (<i>third revision</i>)