

AMENDMENT NO. 1 JULY 1990
TO
IS 7086 (Part 1) : 1973 METHODS OF SAMPLING
AND TEST FOR RUBBER COMPOUNDING
INGREDIENTS, PART 1

(*Page 4, clause 3.1.1*) — Substitute the following for the existing clause:

'3.1.1 Gallie Porritt Sieve — The apparatus (Fig. 1) consists of a funnel made of copper terminating at the foot in a short cylindrical outlet, in which is inserted a shallow removable cup. To the bottom of the cup, a wire gauze of the required size of 25 mm diameter is soldered. Water under pressure of 150 to 350 kN/m² (approximately 1.5 to 3.5 kgf/cm²) is supplied by a tube fitted with a nozzle designed to discharge a spreading jet throughout the wire gauze, and the tube is so arranged that the distance of the orifice in relation to the wire gauze may be adjusted. The tube should be made of brass or any other material which is not likely to corrode. The tube is provided with a filter to ensure removal of any solid particles from the water. A second tube which is also provided with a filter is improvized to supply a gentle stream of water for wetting the powder and for supplying more water to the funnel during the progress of the test.'

(*Page 4, clause 3.2.1, line 15*) — Substitute '105+2°C' for '100°C.'

(*Page 6, clause 3.2.2*) — Insert the following at the end:

'The wetting agent should be free from grit.'

(PCD 13)