

AMENDMENT NO. 1 JUNE 1997
TO
IS 7151 : 1991 CORRUGATED FIBREBOARD BOXES
FOR PARA-DROPPING OF SUPPLIES —
SPECIFICATION
(First Revision)

(*Cover page, Title*) — Insert the words '(*First Revision*)' below the word 'SPECIFICATION'.

(*Page 1, clause 2.1*)— Substitute the following for the existing clause:

'2.1 The Indian Standards listed below contain provisions which through reference in this text, constitute provisions of this Indian Standard. At the time of publication, the editions indicated were valid. All standards are subject to revision, and parties to agreements based on this Indian Standard are encouraged to investigate the possibility of applying the most recent editions of the Indian Standards indicated below:

<i>IS</i>	<i>No.</i>	<i>Title</i>
1060 (Part 1) : 1966		Methods of sampling and test for paper and allied products : Part 1 (<i>revised</i>)
2771 (Part 1) : 1990		Corrugated fibreboard boxes : Part 1 General requirements (<i>second revision</i>)
4006 (Part 1) :	1985	Methods of test for paper and pulp based packaging materials : Part 1 (<i>first revision</i>)
4006 (Part 2) : 1985		Methods of test for paper and pulp based packaging materials : Part 2 (<i>first revision</i>)
4084 : 1978		Eyelets and washers (<i>first revision</i>)
4261 : 1967		Glossary of terms relating to paper and pulp based packaging materials
5177 : 1985		Jute lines and ropes (<i>second revision</i>)
7028 (Part 4) : 1987		Performance tests for complete filled transport packages : Part 4 Vertical impact drop test (<i>first revision</i>)'

Amend No. 1 to IS 7151 : 1991

(Page 1, clause 3.1, line 3) — Substitute '1990' for '1977'.

(Page 1, clause 4.3, line 2) — Substitute '1985' for '1969'.

(Page 1, clause 5.3, last sentence) — Delete.

(Page 2, clause 7.2) — Insert the following new clauses after the 7.2 (d):

'e) Puncture Resistance

When tested by the method given in 9 of IS 4006 (Part 2) : 1985, the average puncture resistance of the corrugated fibre board shall be not less than 150 cm.kg. The average shall be based on at least 4 determinations on unscored areas. No individual reading shall be less than 135 cm.kg. One test shall be made in such a manner that the corrugation of the combined board run in the same plane as the puncture arm and one test with corrugations at right angle to the first test. Such tests shall be made from both sides of the board.

7.3 Corrugated fibreboard box shall satisfy the following tests:

a) Compression Strength

The average compression strength of the box in the top to bottom direction, when determined in accordance with IS 7028 (Part 4) : 1987 shall be not less than 650 kg at a deflection of not more than 15 mm. The average shall be based on 5 determinations.

b) Flap Bend Test

The flaps of the box shall be capable of being folded through 180° inside and then 180° outside along the line of creasing without cracking of the board or facing.'

(CHD 016)