



AMENDMENT NO. 1 JULY 1983

TO

IS:7174-1974 SPECIFICATION FOR CARBON STEEL TUBES
FOR USE ON BOARD SHIPS FOR WORKING PRESSURES
0.7 to 1.7 N/mm²

Alterations

(Page 5, clause 6.1.1) - Substitute the following
for the existing clause:

'6.1.1 The ladle analysis of the steel for tubes
shall not show sulphur and phosphorus in amount
exceeding 0.050 percent each and the carbon content
shall be 0.20 percent, Max.'

6.1.2 The ladle analysis of steel shall be carried
out either by the method specified in IS:228* and its
relevant parts or any other established instrumental/
chemical method. In case of dispute the procedure
given in IS:228* and its relevant parts shall be
referee method. However, where the method is not
given in IS:228* and its relevant parts, the referee
method shall be agreed to between the purchaser and
the manufacturer.'

(Page 5, clause 6.1.1.1) - Substitute '6.1.2.1'
for '6.1.1.1'.

(Page 5, foot-note with '*' mark) - Substitute
the following for the existing foot-note:

'*Methods for chemical analysis of steels
(issued in several parts).'

(SMDC 22)