

AMENDMENT NO. 1 JUNE 2017
TO
IS 7283 : 1992 HOT-ROLLED BARS FOR THE
PRODUCTION OF BRIGHT BARS AND MACHINED
PARTS FOR ENGINEERING APPLICATIONS —
SPECIFICATION

(First Revision)

(Cover page and Page 1, Title) — Substitute the following for the existing title:

**‘HOT-ROLLED BARS AND RODS FOR THE PRODUCTION OF
BRIGHT BARS AND MACHINED PARTS FOR ENGINEERING
APPLICATIONS — SPECIFICATION’**

(Page 1, clause 1.1) — Substitute the following for the existing clause:

‘1.1 This standard covers the requirements of hot rolled bars and rods for the production of bright bars by cold drawing, turning or grinding or a combination of these processes and also for production of machined parts for engineering applications.’

(Page 1, clause 1.1.1) — Substitute the following for the existing clause:

‘1.1.1 This standard does not cover the requirement for alloy steels’.

(Page 1, clause 4.2, line 1) — Insert ‘and rods’ between ‘bars’ and ‘may’.

(Page 1, clause 4.4, line 1) — Insert ‘and rods’ between ‘bars’ and ‘should’.

(Page 2, clause 6.1, line 1) — Insert ‘and rods’ between ‘The bars’ and ‘shall’.

(Page 2, clause 6.1.1, line 1) — Insert ‘and rods’ between ‘The hot rolled bars’ and ‘should’.

(Page 2, Table 1, Heading) — Insert ‘and rods’ in the end.

Amendment No. 1 to IS 7283 : 1992

(Page 2, clause 7.1, lines 1 to 3) — Substitute the following for the existing clause:

‘7.1 Hot-rolled steel bars and rods shall be manufactured to any of the sizes 5 mm and above as agreed to between the manufacturer and the purchaser.’

(Page 2, clause 7.1, lines 4 to 10) — Delete.

(Page 2, clause 7.1.1) — Delete.

(Page 2, clause 8) — Substitute the following for the existing clause:

‘8 DECARBURIZATION

Total depth of decarburization when tested as per IS 6396:1983 for hot-rolled bars and rods shall be 1.5 percent maximum of the diameter per side and 2.0 percent maximum in the annealed condition.’