

AMENDMENT NO. 3 NOVEMBER 1998
TO
IS 7316 : 1974 SPECIFICATION FOR DECORATIVE
PLYWOOD USING PLURALITY OF VENEERS FOR
DECORATIVE FACES

(Page 7, clause 9.1.2.1) — Substitute the following for the existing:

‘9.1.2.1 Three test specimens of size 150 mm × 150 mm shall be prepared from each of the boards selected and submerged in water at $60 \pm 2^{\circ}\text{C}$ for a period of 3 hours and dried for 8 hours at a temperature of $60 \pm 2^{\circ}\text{C}$ and then followed by two more cycles of soaking and drying under same conditions described above.’

(CED 20)

Reprography Unit, BIS, New Delhi, India