

AMENDMENT NO. 4 JANUARY 2005
TO
IS 7316 : 1974 SPECIFICATION FOR
DECORATIVE PLYWOOD USING PLURALITY OF
VENEERS FOR DECORATIVE FACES

(Page 5 and 6, clause 7) — Substitute the following for the existing:

7 DIMENSIONS AND TOLERANCES

7.1 The dimensions of plywood boards shall be as follows:

2 400 mm × 1 200 mm	2 400 mm × 900 mm
2 100 mm × 1 200 mm	2 100 mm × 900 mm
1 800 mm × 1 200 mm	1 800 mm × 900 mm
1 500 mm × 1 200 mm	1 500 mm × 900 mm
1 200 mm × 1 200 mm	1 200 mm × 900 mm
900 mm × 900 mm	

7.2 Thickness

The thickness shall be 3 mm, 4 mm, 5 mm, 6 mm, 9 mm, 12 mm, 19 mm and 25 mm.

NOTE — Any other dimensions (length, width and thickness) as agreed to between the manufacturer and the purchaser may also be used.

7.3 Tolerances

Tolerances on the nominal sizes of finished boards shall be as given below:

<i>Dimension</i>	<i>Tolerance</i>
Length	+6 -0 mm
Width	+3 -0 mm

Thickness:

- | | |
|--------------------|-------------|
| i) Less than 6 mm | ±10 percent |
| ii) 6 mm and above | ±5 percent |

Amend No. 4 to IS 7316 : 1974

Edge straightness	2 mm per 1 000 mm or 0.2 percent
Squareness	2 mm per 1 000 mm or 0.2 percent

NOTE — Edge straightness and squareness shall be tested as per Annex A.

(Page 9, clause 13.1) — Insert the following Annex A after clause 13.1:

ANNEX A **(Clause 7.3)**

METHOD OF TEST FOR EDGE STRAIGHTNESS AND SQUARENESS

A-1 PROCEDURE FOR EDGE STRAIGHTNESS

A-1.1 The straightness of the edges and ends of plywood shall be verified against a straight edge not less than the full length of the plywood. If the edge on the end of the plywood is convex, it shall be held against the straight edge in such a way as to give approximately equal gap at each end. The largest gap between the straight edge and the edge shall be measured to the nearest millimetre and recorded.

A-2 PROCEDURE FOR SQUARENESS

A-2.1 The squareness of plywood shall be checked with a 1 200 mm × 1 200 mm square, by applying one arm of the square to the plywood. The maximum width of the gap shall be recorded.

NOTE — Any other dimensions (length, width and thickness) as agreed to between the manufacturer and the purchaser may also be used.

7.3 Tolerances

Tolerances on the nominal sizes of finished boards shall be as given below:

<i>Dimension</i>	<i>Tolerance</i>
Length	+6 - 0 mm
Width	+3 - 0 mm
Thickness:	
i) Less than 6 mm	±10 percent
ii) 6 mm and above	±5 percent