

AMENDMENT NO. 1 NOVEMBER 2021

TO

IS 7328 : 2020 SPECIFICATION FOR POLYETHYLENE MATERIAL FOR MOULDING AND EXTRUSION

(*Second Revision*)

(*First cover page, Hindi title*) — Substitute ‘दूसरा पुनरीक्षण’ for ‘तीसरा पुनरीक्षण’

(*First cover page, English title*) — Substitute ‘*Second Revision*’ for ‘*Third Revision*’

(*Foreword, Para 1, line 1*) — Substitute ‘*Second Revision*’ for ‘*Third Revision*’

(*Page 1, Title*) — Substitute ‘*Second Revision*’ for ‘*Third Revision*’

(*Page 6, clause 5.5.2*) — Substitute the following for the existing clause:

‘**5.5.2** When the products are used in contact with foodstuffs, pharmaceuticals and drinking water, its requirements with respect to the material shall also comply with Annex D.’

(*Page 10, Annex A*) — Insert the following Indian Standards at the end of the list of referred Standards:

‘ IS 9833 : 2018	List of colourants for use in plastics in contact with foodstuffs and pharmaceuticals (<i>second revision</i>)
IS 9845: 1998	Determination of overall migration of constituents of plastics materials and articles intended to come in contact with foodstuffs — Method of analysis (<i>second revision</i>)’

(Page 13, Annex C) — Insert the following new Annex D after Annex C:

‘ANNEX D

(Clause 6.4.2)

D-1 PIGMENTS AND COLOURANTS

In case the coloured material is used for food-packaging applications it shall comply with the list and limits of the pigments and colourants prescribed in IS 9833.

D-2 OVERALL MIGRATION

The material shall comply with the overall migration limits as detailed below when tested by the method prescribed in IS 9845.

- a) 60 mg/kg, *Max* of the foodstuff; in the case of liquid foodstuffs or of simulants, the limit shall be 60 mg/l, *Max*. However, the value of the overall migration limit shall be equal to 10 mg/dm² of the surface of the material or article in the following cases:
 - 1) Containers or articles which are similar to containers or which in any case may be filled to a capacity less than 250 ml provided it is possible to calculate the surface area of contact with the foodstuff.
 - 2) Sheets, foils and other non-fillable articles for which ratio between the surface area of the material or article and the quantity of foodstuffs, in contact may not be calculated.

D-3 STORAGE AND CONTROL

D-3.1 Storage

Plastics materials intended for food contact use shall be stored separately from materials in closed, properly identified containers.

D-3.2 Control

An authorized person shall supervise and control the issue of plastics materials to the process or manufacturing area and shall maintain appropriate records of the issue of such materials.

D-3.3 Adequate standards of hygiene shall be maintained at all times and plant operators and store men shall be trained in proper hygiene practices.’

(PCD 12)