

AMENDMENT NO. 1 JUNE 2024

TO

IS 16373 : 2015 LEAD ACID STORAGE BATTERIES FOR MOTOR VEHICLES — VALVE REGULATED TYPE

(First Revision)

(Page 3, clause 6.1.3, para 2) — Substitute following for the existing:

‘If the final battery temperature is different from $25\text{ }^{\circ}\text{C} \pm 2\text{ }^{\circ}\text{C}$, the following temperature correction formula shall be used:

$$C_e\text{ }25\text{ }^{\circ}\text{C} = C_eT [1 - 0.01(T - 25)]'.$$

(Page 6, Table 2) — Substitute following for the existing:

Table 2 Endurance Test Sequence

(Clause 6.6.5)

SI No.	Test	Battery Class	
		A	B
(1)	(2)	(3)	(4)
i)	Corrosion	x	x
ii)	Cycling 1 or 3 (40 °C)	x	-
iii)	Cycling 2	-	x

(Page 7, clause 6.10.1, line 2) — Substitute ‘I_n’ for ‘I_s’.

(Page 3, Table 1) — Substitute following for the existing:

SI No.	Test	Battery					
		1	2	3	4	5	6
(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)
i)	1 st 20h Capacity (6.1)	x	x	x	-	-	-
ii)	1 st Reserve capacity (6.2)	-	-	-	x	x	x
iii)	1 st Cranking performance (6.3.1)	x	x	x	x	x	x
iv)	2 nd 20h Capacity (6.1)	x	x	x	-	-	-
v)	2 nd Reserve capacity (6.2)	-	-	-	x	x	x
vi)	2 nd Cranking performance (6.3.1)	x	x	x	x	x	x
vii)	3 rd 20h Capacity (6.1)	x	x	x	-	-	-
viii)	3 rd Reserve capacity (6.2)	-	-	-	x	x	x
ix)	3 rd Cranking performance (6.3.1)	x	x	x	x	x	x
x)	Endurance test (corrosion test) (6.6)	x	-	-	-	-	-
xi)	Endurance test (cycling test) (6.6)	-	x	-	-	-	-
xii)	Charge retention (6.5)	-	-	-	x	-	-

Sl No.	Test	Battery					
		1	2	3	4	5	6
(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)
xiii)	Charge acceptance (6.4)	-	-	x	-	-	-
xiv)	Electrolyte retention (6.8)	-	-	-	x	-	-
xv)	Vibration resistance (6.7)	-	-	-	-	x	-