

AMENDMENT NO. 3 OCTOBER 2024

TO

IS 16513 : 2016 AGRO TEXTILES — INSECT NETS FOR AGRICULTURE AND HORTICULTURE PURPOSES — SPECIFICATION

(Page 2, Table 1) — Substitute the following for the existing:

Table 1 Requirements of Insect Nets

(Clause 6.2)

Sl No.	Characteristic(s)	Requirements				Tolerance	Method of Test, Ref to
		Type I 30 mesh	Type II 40 mesh	Type II A 40 mesh	Type III 50 mesh		
(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)
i)	Mass, g/m ²	90	105	125	125	± 5 percent	IS 1964
ii)	a) Ends per inch	30	40	40	50	± 2	IS 1963
	b) Picks per inch	24	24	32	24	± 2	
iii)	Cover factor, percent, <i>Min</i>	30	40	45	50	—	Annex B
iv)	Breaking strength of insect nets fabric before UV exposure (ravelled strip method 325 mm × 70 mm) ¹⁾ , kg, <i>Min</i>					—	IS 1969 (Part 1)
	a) Warpway	80	120	120	140		
	b) Weftway	50	65	80	70		
v)	Retention in breaking strength after UV exposure, kg, <i>Min</i>	← 85 percent of original actual value of fabric →					Annex C and IS 1969 (Part 1)
vi)	Bursting strength, kg/cm ² , <i>Min</i>	10	18	19	20	—	IS 1966 (Part 1) or IS 1966 (Part 2)
vii)	Air permeability in mm/s at 50 pascal water head pressure, <i>Min</i>	6 500	5 000	4 000	3 000	—	IS 11056

¹⁾ Width after ravelling = 50 mm, Gauge length = 200 mm.