

AMENDMENT NO. 2 FEBRUARY 2021

TO

IS 16703 : 2017 TEXTILES — HIGH DENSITY POLYETHYLENE (HDPE) / POLYPROPYLENE (PP) WOVEN SACKS FOR PACKAGING OF 25 KG POLYMER MATERIALS — SPECIFICATION

(Page 1, clause 4.2) — Substitute the following for the existing clause:

‘4.2 Fabric

The fabric used in the manufacture of HDPE/PP woven sacks shall be woven as a tube on circular loom from HDPE/PP tapes having width of 2.5 mm (tolerance of ± 5 percent) conforming to IS 6192 and IS 11197 respectively. The linear density of tapes shall be 900 denier for 10×10 mesh fabric. The un-laminated fabric mass shall be 79 g/m^2 with a tolerance of ± 3 percent. For specific applications, necessitating higher fabric mesh, the tape linear density shall be maintained accordingly. The denier of HDPE/PP tapes used in the manufacture of woven fabric shall be subjected to the following tolerances:

- a) ± 10 percent on individual value, and
- b) ± 5 percent on average.

The construction particulars of fabric shall be as given in Table 1.’

(Page 3, Note 2 under Table 1) — Substitute the following for the existing note:

‘2 The buyer and the seller may agree to the unlaminated fabric weight per square metre other than those specified in 4.2 and the fabric mesh other than those specified in Table 1. However, the tolerance on agreed weight of the unlaminated fabric shall be ± 3 percent and tolerance on agreed ends per dm and picks per dm shall be ± 2 .’