

AMENDMENT NO. 3 JUNE 2025
TO
IS 16709 : 2017 TEXTILES — POLYPROPYLENE (PP) WOVEN,
LAMINATED, BLOCK BOTTOM VALVE SACKS FOR PACKAGING OF 50 KG
CEMENT — SPECIFICATION

[Page 4, Table 1, Sl No. (v) and (vii)] — Substitute the following for the existing:

Sl No.	Characteristic	Requirement	Tolerance	Method of Test, Ref to
(1)	(2)	(3)	(4)	(5)
v)	Average breaking strength of fabric, (ravelled strip method, 325 mm × 70 mm ¹⁾), <i>Min</i> , N ²⁾ (kgf)			IS 1969 (Part 1)
	a) Lengthwise			
	i) Air permeability less than 100 m³/h at 50 mbar	650 (66)	-	
	ii) Air permeability value between 100 m³/h to 110 m³/h at 50 mbar	550 (56)	-	
	iii) Air permeability value between 111 m³/h to 120 m³/h at 50 mbar	530 (54)	-	
	iv) Air permeability value between 121 m³/h to 130 m³/h at 50 mbar	520 (53)	-	
	v) Air permeability value more than 130 m³/h at 50 mbar	510 (52)	-	
	b) Widthwise			
	i) Air permeability less than 100 m³/h at 50 mbar	600 (61)	-	
	ii) Air permeability value between 100 m³/h to 110 m³/h at 50 mbar	530 (54)	-	
	iii) Air permeability value between 111 m³/h to 120 m³/h at 50 mbar	520 (53)	-	
	iv) Air permeability value between 121 m³/h to 130 m³/h at 50 mbar	510 (52)	-	
	v) Air permeability value more than 130 m³/h at 50 mbar	500 (51)	-	
vii)	Average breaking elongation of fabric (ravelled strip method), percent			
	a) Lengthwise	10 to 20	-	
	b) Widthwise	10 to 20	-	

(Page 4, Table 1, Note 2) — Substitute the following for the existing:

‘2 The mass of the sack as specified above is of unprinted sack. The mass of the printed ink on sack will depends on the artwork and shall be as agreed to between the buyer and the seller. The mass of the sack with dimensions other than those specified above shall be calculated by the method given in Annex G which is for guidance only.’

Price Group 1

Amendment No. 3 to IS 16709 : 2017

(Page 8, clause **D-3.1**) — Substitute the following for the existing:

‘D-3.1 Drop test shall be carried out using suitable sack drop mechanism. Each sack shall be dropped from a height of 1.8 m for the test requirements as specified below:

- a) Height of drop = 1.8 m, (one time for face side and one times for back side); and
- b) Height of drop = 1.8 m (one time for left edge and one time for right edge).’

(Page 8, clause **D-3.2**) — Insert the following at the end:

‘D- 3.3 Three sack (as test specimens) shall be tested by following the procedure as laid down in **D-3.1** for conformity of each sample. All three sack, when dropped, shall conform to the criteria as specified in **D-4.**’