

AMENDMENT NO. 1 NOVEMBER 2019

TO

**IS 16715 : 2018 ULTRAFINE GROUND GRANULATED
BLAST FURNACE SLAG — SPECIFICATION**

(Page 1, Table 1, Note) — Substitute the following for the existing:

‘NOTES

1 For the purpose of testing of UGGBS as per IS 4032, wherever reference to cement has been made in IS 4032, it may be read as UGGBS.

2 UGGBS shall satisfy any one of the two requirements given at SI No. (viii) and (ix).

3 $\text{CaS} = 2.25 \times \text{Sulphide sulphur}$. Sulphide sulphur in GGBS may be estimated as per the method specified in IS 4032, assuming total sulphide sulphur exists as CaS.’

(Page 2, Table 2) — Substitute the following for the existing table:

Table 2 Physical Requirements of UGGBS

(Clause 6)

SI No.	Characteristic	Requirement	Method of Test, Ref to
(1)	(2)	(3)	(4)
i)	Fineness, m^2/kg , <i>Min</i> (optional) (<i>see</i> Note 1) BET Method (Nitrogen adsorption)	1 500	IS 11578
ii)	Particle size, μm , <i>Max</i> (<i>see</i> Note 2) :		Using laser diffraction PSD analyzer
	a) D_{50}	5	
	b) D_{95}	15	
iii)	Slag activity index :		<i>See</i> Note 3
	a) 7 days	Not less than 85 percent	
	b) 28 days	Not less than 100 percent	

NOTES

- 1** By agreement between the purchaser and the manufacturer, the fineness test may be carried out in accordance with the method given in IS 11578.

- 2 D_{95} indicates that 95 percent of the particles on a mass basis are below a given size while D_{50} indicates that 50 percent of the particles on a mass basis are below a given size.
- 3 Slag activity index (SAI) shall be determined using blend of 50 percent UGGBS and 50 percent control OPC 43 conforming to IS 269, having total alkalis ($\text{Na}_2\text{O} + 0.658 \text{ K}_2\text{O}$) not less than 0.6 percent and not more than 0.9 percent. The blend shall be tested for compressive strength by casting and testing prisms, in accordance with IS 4031(Part 8). The mortar mix proportions by mass are, 1 part of the cement blend under test, 3 parts of standard sand and 0.5 part of water.

SAI shall be determined as:

$$\frac{\text{compressive strength of the motor cube using blend}}{\text{compressive strength of control OPC motor cube}} \times 100$$
