

AMENDMENT NO. 1 JULY 2024

TO

IS 16725 : 2018 TEXTILES — TACTICAL 3 POINTS SLING UNIVERSAL — SPECIFICATION

(Page 1, Table 1) — Substitute the following for existing:

Sl No.	Particular	Approximate Resultant Denier of Yarn (For Guidance Only)	Tenacity of Single Ply Yarn, g/Denier, <i>Min</i>
(1)	(2)	(3)	(4)
i)	Warp	840	5.0
ii)	Weft	840	5.0
iii)	Binding end	840	5.0
iv)	Method of test, ref to	IS 7703 (Part 1)	IS 7703 (Part 2)
NOTES			
1 Number of ends in full width shall not be less than 219 (ground = 206 and binding 13) when tested as per method prescribed in Annex B of IS 14968.			
2 Number of picks/dm shall not be less than 198 when tested as per method prescribed in Annex B of IS 14968.			

[Page 2, Table 2, Sl No. (iii), col (4)] — Substitute ‘Annex B of IS 4727’ for ‘Appendix A of IS 4727’.

(Page 10, Annex A) — Delete ‘references of IS 766 and IS 2454’.

(Page 10, Annex A) — Insert the following references:

<i>‘IS No.</i>	<i>Title</i>
IS/ISO 105-B02 : 2014	Textiles — Tests for colour fastness: Part B02 Colour fastness to artificial light: Xenon arc fading lamp test
IS/ISO 105-X12 : 2016	Textiles — Tests for colour fastness: Part X12 Colour fastness to rubbing (<i>first revision</i>)
IS 7703	Methods of test for man-made fibres continuous filament flat yarn:
(Part 1) : 1990	Linear density (<i>first revision</i>)
(Part 2) : 1990	Dry and wet tenacity and elongation (<i>first revision</i>)
IS 14968 : 2015	Textiles — High density polyethylene (HDPE)/polypropylene (PP) woven sacks for packaging 50 kg/25 kg sugar — Specification (<i>first revision</i>)’.