

AMENDMENT NO. 1 JULY 2025
TO
IS 16983 : 2024 SOLID BLEACHED SULPHATE BOARD — SPECIFICATION
(First Revision)

[Page 1, clause 4(a)] — Substitute the following for existing:

‘a) Top coating — The coating grammage (combined pre-coat and post-coat) shall be (25 ± 5) gsm’.

(Page 2, clause 5.6) — Substitute the following for existing:

‘The material when supplied in printed mode, shall pass for the print resistance and ink adhesions when tested in accordance with the Annex B and Annex C respectively of this standard.’

(Page 2, clause 5.10.1) — Substitute the following for existing:

‘In case of direct food contact usage, the paper board shall confirm to IS 1776 or IS 12999 except for the requirement of grammage. In addition, the paper board shall be OBA (optical brightening agent) free when tested in accordance with EN 648 till a relevant Indian Standard/ method is developed. Further, anthraquinone shall not be used for making paper board. CEN/TS 17630 : 2021 ‘Pulp, paper and paperboard — Determination of anthraquinone in extracts from pulp, paper and paperboard’ shall be used till a relevant Indian Standard/method is developed to determine presence of anthraquinone during paper board making.’

[Page 3, Table 1, Sl No. (i), col 2] — Substitute ‘Bulk, cc/g, *Min*’ for ‘Bulk, cc/g’.

[Page 3, Table 1, Sl No. (i), col 3] — Substitute ‘1.15 (*see* Note 1)’ for ‘1.15 to 1.25’.

(Page 3, Table 1) — Insert the following Note at the end of the Table 1:

‘NOTE — The bulk shall be as agreed to between the purchaser and supplier. No single test result shall vary by more than ± 0.05 cc/g from the declared bulk when tested in accordance with IS 1060 (Part 5/Sec 3). The minimum bulk shall however be 1.15 cc/g.’

[Page 3, Table 1, Sl No. (v), col 2] — Substitute ‘Brightness, Indoor C/2°, percent, *Min* (*see* Note 2)’ for ‘Brightness, Indoor C/2°, percent, *Min*’.

(Page 3, Table 1) — Insert the following Notes at the end of the Table 1:

‘NOTES

1 The bulk shall be as agreed to between the purchaser and supplier. No single test result shall vary by more than ± 0.05 cc/g from the declared bulk when tested in accordance with IS 1060 (Part 5/Sec 3). The minimum bulk shall however be 1.15 cc/g.

2 The brightness requirement shall not be applicable for material intended for packaging food items.’

[Page 3, Table 1, Sl No. (v), col 3] — Substitute ‘82’ for ‘88’.

[Page 4, Table 3, Sl No. (iii)] — Substitute the following for existing:

iii)	Wax pick number:	IS 1060 (Part 3)
	a) Coated surface	—
	b) Uncoated or bottom surface	No pick at 12A

(CHD 16)

Price Group 1
Publication, BIS, New Delhi