

AMENDMENT NO. 1 SEPTEMBER 2021

TO

**IS 17048 : 2018 HALOGEN FREE FLAME RETARDANT
(HFFR) CABLES FOR WORKING VOLTAGES UP TO
AND INCLUDING 1 100 V — SPECIFICATION**

(Page 4, clause 5.7, line 4) — Substitute ‘Annex D’ for ‘Annex 4’.

(Page 18, Annex A, Sl No. 9, col 4) — Substitute ‘Annex D’ for ‘Annex 4’.

(Page 20, Annex B, SI No. 2.2) — Substitute the following for the existing:

Sl.No	Test	Unit	Test Method	Type of Sheathing			
				HFS-TP 70	HFS-TP 90	HFS-XL70	HFS-XL90
(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)
2.2	Properties after ageing in air oven						
	Ageing conditions:						
	– temperature	°C		80 ± 2	100 ± 2	100 ± 2	100 ± 2
	– duration of treatment	h		168	168	168	168
	Value to be obtained for the tensile strength:						
	– <i>Min</i>	N/mm ²	IS 10810 (Part 11)	10	10	7	10
	– variation, <i>Max</i>	%		±25	± 40	±30	± 40
	Values to be obtained for the elongation at break:						
	– <i>Min</i>	%		100	100	125	100
	– variation, <i>Max</i>	%		± 25	± 40	± 30	± 40

(Page 28, Annex D, clause **D-2.4.2**, line 2) — Substitute ‘**D-2**’ for ‘**D-5**’.